



# EcoPrimer®

Άχρωμο, άοσμο, διεισδυτικό, ακρυλικό αστάρι τοιχοποιίας

## περιγραφή

Το EcoPrimer είναι άχρωμο ακρυλικό αστάρι τοιχοποιίας, για εσωτερικές ή εξωτερικές επιφάνειες. Διεισδύει σε πορώδεις ή ελαφρώς αποσπασθωμένες επιφάνειες, για μείωση της απορρόφησης και σταθεροποίηση. Ασταρώνει – σταθεροποιεί παλιά υδροχρώματα ή άλλες παρόμοιες βαφές. Εφαρμόζεται σε καινούργιο μπετόν ή τσιμεντοκονίαμα (ακόμη και νεότερα των 30 ημερών) με pH μέχρι 13.

## ΤΕΧΝΙΚΑ ΧΑΡΑΚΤΗΡΙΣΤΙΚΑ

Ειδικό βάρος: 1.0 (kg/L)	Ιξώδες: ford cup #4, 12s
Ποσοστό στερεών κατά όγκον: 15 ± 1	Τύπος φορέα: 100% ακρυλικό
Ποσοστό στερεών κατά βάρος: 15 ± 1	Σημείο ανάφλεξης: μη αναφλέξιμο
Καλυπτικότητα: περίπου 10m <sup>2</sup> /L. Εξαρτάται από την απορροφητικότητα και την υφή της επιφάνειας.	Οδηγία Ευρωπαϊκής Ένωσης για οριακή τιμή μέγιστης περιεκτικότητας σε Π.Ο.Ε για αυτό το προϊόν: (Κατ.Α/η) 50g/l(2007) / 30g/l(2010). Αυτό το προϊόν περιέχει μέχρι 25g/l Π.Ο.Ε

## οδηγίες χρήσης

**Προδιαγραφές εφαρμογής:** Σε μπετόν, σοβά, τσιμεντόλιθους: 1 χέρι EcoPrimer, 2-3 χέρια κατάλληλης βάρφης.

**Εφαρμογή:** Κατάλληλη θερμοκρασία: 5°C ελάχιστη, 38°C μέγιστη (θερμοκρασία αέρα, επιφάνειας και υλικού) και τουλάχιστον 3°C πάνω από το όριο συμπύκνωσης υδρατμών.

- > Σχετική υγρασία: μέχρι 85%
- > Καθαριστικό: νερό
- > Αραίωση: δεν συστήνεται. Το προϊόν είναι έτοιμο για χρήση
- > Πινέλο: νάιλον ή πολυέστερ
- > Ρολό: συνθετικό 10-20 mm
- > Σφουγγάρι βαψίματος: συνθετικό
- > Σπρέι: πίεση 700-100psi, ακροφύσιο (μπέκο) 0.017

**Στέγνωμα:** Σε θερμοκρασία 25°C και σχετική υγρασία 50%.

- > Επιδέχεται άγγιγμα: 1 ώρα
- > Επιπρόσθετα χέρια: 3 ώρες

**Τελική βαφή:** Κατάλληλες βαφές – ProMar 200 Interior & Exterior Emulsion Paint, ProMar 200 Semi-Gloss Emulsion Paint, ProMar 200 Highlights, Everclean Ακρυλική βαφή τοίχων (μάτ ή ασπινέ), LOXON Ακρυλική Ελαστομερής βαφή, HealthSpec, Διακοσμητικές βαφές Pelelac.

**Προσοχή:** Να μην εφαρμόζεται σε υγρή επιφάνεια. Δεν σταθεροποιεί βαριά αποσπασθωμένες επιφάνειες. Να μην στοιβάζεται τόσο EcoPrimer ώστε να γυαλίζει η επιφάνεια.

## μέτρα προστασίας και ασφάλειας

Να αποφεύγεται η έκθεση του υλικού σε άμεση ηλιακή ακτινοβολία και ακραίες θερμοκρασίες, κατά την αποθήκευσή του.

- > Το υλικό να κρατείται μακριά από παιδιά.
- > Πιτσιλιές στα μάτια να ξεπλένονται αμέσως με άφθονο νερό και να ζητείται ιατρική συμβουλή.
- > Σε περίπτωση ρύπανσης του δέρματος να καθαρίζεται με σαπούνι και νερό.
- > Σε περίπτωση κατάποσης να ζητείται αμέσως ιατρική συμβουλή, δείχνοντας το δοχείο.
- > Η εφαρμογή να γίνεται σε καλά αεριζόμενους χώρους.

**Συσκευασία:** 1,4 και 20 L.

**Αποθήκευση:** Σε στεγνό μέρος, μακριά από ακραίες θερμοκρασίες. Χρόνος αποθήκευσης: δεν ορίζεται.

**Σημείωση:** Οι πληροφορίες που δίνονται για τα προϊόντα μας δια μέσου των τεχνικών φυλλαδίων ή οδηγιών χρήσης, από τους υπαλλήλους, αντιπροσώπους ή προμηθευτές μας, είναι βασισμένες σε εκτενή έρευνα και πολλά χρόνια πείρας και δίνονται για σκοπούς ενημέρωσης. Εγγυώμαστε τη σταθερά υψηλή ποιότητα των προϊόντων μας αλλά δεν φέρουμε καμία ευθύνη για οποιαδήποτε ζημιά ή απώλεια παρουσιασθεί στους χώρους των εργοταξίων, εφόσον το τελικό αποτέλεσμα εξαρτάται και από παράγοντες που ξεφεύγουν από τον έλεγχο της εταιρείας.





# EcoPrimer®

Clear, odorless, penetrative, acrylic stabilizer / surface conditioner

## description

EcoPrimer is an acrylic stabilizer/surface conditioner, for interior and exterior surfaces. It will penetrate and seal porous or lightly chalky building surfaces. It stabilizes surfaces already painted with old distempers or similar paints. It adheres to new concrete or plaster (even prior to a 30 day cure) with a pH up to 13.

## technical characteristics

Specific gravity: 1.0 (kg/L)	Viscosity: Ford cup #4, 12s
Volume solids: 15 ± 1	Vehicle type: 100% acrylic
Weight solids: 15 ± 1	Ignition point: non-combustible
Coverage: approximately 10m <sup>2</sup> /L, depending on porosity and texture of surface.	European Union Limit for this product: (Cat A/h) 50g/l (2007) / 30g/l (2010). This product contains max 25g/l V.O.C.

## instructions for use

**Application characteristics:** On concrete, plaster, block: 1 coat EcoPrimer, 2-3 coats appropriate topcoat.

**Application:** Temperature: 5°C minimum, 38°C maximum (air, surface and material) at least 3°C above point.

- > Relative humidity: 85% maximum
- > Clean up: water
- > Reduction: no reduction recommended – ready to use product.
- > Brush: nylon / polyester
- > Roller: 10–20 mm nap synthetic cover
- > Pad: synthetic
- > Spray – Airless: pressure 700–1000 psi, tip 0.017

Changes in pressure and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compatible with existing environmental and application conditions. After drying, repeat it necessary.

**Drying:** At 25°C and 50% RH.

- > Touch dry: 1 hour
- > Recoatable: 3 hours

**Recommended topcoats:** Suitable topcoats – ProMar 200 Interior & Exterior Emulsion Paint, ProMar 200 Semi-Gloss Emulsion Paint, ProMar 200 Highlights, Everclean Acrylic Wall Paint (flat or satin), LOXON Acrylic Elastomeric Coating, HealthSpec, Pelelac decorative paints.

**Caution:** Do not apply on damp surfaces or over heavy chalked surfaces. Do not build up a surface glaze.

## health and safety measures

- > Avoid direct sunlight & high temperature during storage.
- > Keep away from children.
- > In case of eye contact contamination flush with large amounts of water and seek medical advice.
- > In case of skin contact wash with soap and water.
- > If swallowed get medical attention immediately, showing the product's package.
- > Apply in well – ventilated spaces.

**Packing:** 1,4 and 20 L.

**Storage:** In dry places, away from extreme temperature. Storage period: not specified.

**Note:** The information supplied in our literature or given by our employees, agents or distributors concerning the use of our products is based upon extensive experience and given in good faith in order to help you. We guarantee the consistent high quality of our products; however, as we have no control over site conditions of the executions of the work, we cannot accept any liability for any loss or damage, which may arise as a result thereof.