


ProMar* 200 Enamel Undercoat



► ΓΕΝΙΚΗ ΠΕΡΙΓΡΑΦΗ

Το ProMar* 200 Enamel Undercoat είναι η καλύτερη επαγγελματική βελατούρα (άντερκοουτ) της εταιρίας Sherwin-Williams Αμερικής. Συστήνεται για χρήση σε επιφάνειες ασταριών (αστάρια ξυλείας, αστάρια μετάλλων, κ.λ.π.), σε εσωτερικούς ή εξωτερικούς χώρους. Το ProMar* 200 Enamel Undercoat βελτώνει την πρόσφυση του ελαιοχρώματος, δεν λεκιάζει και γυαλοχαρτίζεται εύκολα.

► ΚΑΛΥΠΤΙΚΟΤΗΤΑ

Καλυπτικότητα: 13 -15 τετραγωνικά μέτρα ανά λίτρο, για κάθε χέρι, σε λεία επιφάνεια.

► ΣΤΕΓΝΩΜΑ

Σε θερμοκρασία 25 °C & σχετική υγρασία 50%:
Επιδέχεται άγγιγμα με το χέρι σε 4 - 5 ώρες.
Μπορεί να γυαλοχαρτιστεί σε 12-16 ώρες.
Επιπρόσθετα χέρια μπορούν να εφαρμοστούν σε 16- 24 ώρες.

► ΤΕΧΝΙΚΑ ΧΑΡΑΚΤΗΡΙΣΤΙΚΑ

Τύπος Φορέα: Αλκυδική Ρητίνη
Ειδικό βάρος: 1.55 ± 0.02
Ποσοστό στερεών κατά όγκον: 41 ± 2%
Ποσοστό στερεών κατά βάρος: 78 ± 2%
Ιξώδες: 2.5 - 3.0 P
Σπιλνότητα: Ματ
Σημείο ανάφλεξης: 43 °C
Χρόνος Αποθήκευσης: 3 χρόνια

► ΠΡΟΕΤΟΙΜΑΣΙΑ ΕΠΙΦΑΝΕΙΑΣ

Καινούριες επιφάνειες: Οι επιφάνειες πρέπει να είναι λείες, στεγνές και καθαρές. Τυχόν στοκαρίσματα πρέπει να έχουν στεγνώσει καλά προηγουμένως. Εφαρμόζονται 1-2 χέρια ProMar* 200 Enamel Undercoat και όταν στεγνώσει γυαλοχαρτίζεται, ξεσκονίζεται και εφαρμόζονται 1-2 χέρια ελαιοχρώματος.
Ήδη βαμμένες επιφάνειες: Για το φρεσκάρισμα ελαιοχρώματος, που είναι σε καλή κατάσταση, δεν χρειάζεται βελατούρα. Καθαρίζεται η επιφάνεια από λάδια, γράσα, σκουριά και ξεφυλλισμένο χρώμα. Πλένεται με απορρυπαντικό, αν χρειάζεται, ξεπλένεται με νερό και αφήνεται να στεγνώσει.
Γυαλιστερές επιφάνειες γυαλοχαρτίζονται με ψιλό γυαλόχαρτο και ξεσκονίζονται. Στα σημεία που χρειάζεται περνιέται βελατούρα (ή και αστάρη) και στο τέλος 1-2 χέρια ελαιοχρώματος. Για αλλαγή χρώματος χρειάζεται ένα χέρι βελατούρα και 1 -2 χέρια ελαιοχρώματος.

► ΕΦΑΡΜΟΓΗ

Συστήνεται όπως το ProMar* 200 Enamel Undercoat χρωματίζεται σε παρόμοια απόχρωση με αυτή του τελικού ελαιοχρώματος. Αραιώνεται, αν χρειάζεται, με νέφτι, μέχρι 10% κατά όγκον. Εφαρμόζεται με πινέλο, ρολό ή σπρέι.

► ΚΑΘΑΡΙΣΜΑ

Πιτσάλιες της βελατούρας καθαρίζονται αμέσως με ρούχο βουτηγμένο σε νέφτι. Τα εργαλεία που χρησιμοποιήθηκαν καθαρίζονται επίσης με νέφτι.

ΣΗΜΕΙΩΣΗ: Οι πληροφορίες που δίνονται για τα προϊόντα μας διαμέσου των τεχνικών φυλλαδίων ή οδηγιών χρήσης, από τους υπαλλήλους αντιπροσώπων ή προμηθευτές μας είναι βασισμένες σε εκτενή έρευνα και πολλά χρόνια πείρας και δίνονται για σκοπούς ενημέρωσης. Εγγυώμαστε τη σταθερά υψηλή ποιότητα των προϊόντων μας αλλά δεν φέρουμε καμιά ευθύνη για οποιαδήποτε ζημιά ή απώλεια παρουσιαστεί στους χώρους των εργασιών, εφόσον το τελικό αποτέλεσμα εξαρτάται και από παραγοντες που ξεφεύγουν από τον έλεγχο της εταιρίας.

► GENERAL DESCRIPTION

ProMar* 200 Enamel Undercoat is Sherwin-Williams' finest undercoat designed for the professional. It is recommended for application on primers (wood primers, metal primers, etc) on interior and exterior surfaces. ProMar* 200 Enamel Undercoat improves adhesion of SuperGloss or Eg-Shel Enamel, has excellent holdout, resists staining and is easy to sand.

► COVERAGE

Sread rate: Smooth surface: 13-15 sp.m./L/coat

► DRYING

@ 25 °C & 50% R.H.:
To touch: 4-5 hours.
To sand: 12-16 hours.
To recoat: 16-24 hours.

► TECHNICAL CHARACTERISTICS

Vehicle type: Alkyd Resin
Specific Gravity: 1.55 ± 0.02
Volume Solids: 41 ± 2%
Weight Solids: 78 ± 2%
Viscosity: 2.5 - 3.0 P
Finish: Mat
Flash Point: 43 °C
Shelf Life: 3 years

► SURFACE PREPARATION

New surfaces: Surfaces shall be smooth, sanded, dry and dust free. Any grease, oil or other foreign material shall be cleaned from the surface before painting. Apply 1 or 2 coats of ProMar* 200 Enamel Undercoat. When dry sand lightly, remove dust and apply 1 or 2 coats of enamel paint (gloss/Eg-Shel).

Previously Painted Surfaces: If in sound condition and of uniform porosity no undercoat is required. Remove rust, dirt, grease and loose or peeling paint from the surface. Wash with a commercial detergent, if required, rinse thoroughly and allow to dry. Dull glossy surfaces with fine sandpaper and clean up sanding dust. Spot prime bare spots and follow with 1 or 2 coats of Enamel Undercoat. For colour changes apply one coat of Undercoat followed by 1 or 2 coats of Enamel Paint.

► APPLICATION

It is recommended that ProMar* 200 Enamel Undercoat is tinted to the approximate shade of the topcoat. Reduce, if required, with white spirit, up to 10% by volume. Apply with brush, roller or spray.

► CLEAN UP

Clean up splatters and painting tools immediately with white spirit.

NOTE: The information supplied in our literature or given by our employees agents or distributors concerning the use of our products is based upon extensive experience and given in good faith in order to help you. We guarantee the consistent high quality of our products. However, as we have no control over site conditions or the execution of the work, we cannot accept any liability for any loss or damage which may arise as a result thereof.

COLOR



Οκτώβρης 2003

PELETICO

PELETICO LTD.

T.Θ. 21326, 1506 Λευκωσία, Κύπρος,
Τηλ.: +357-22482265, Φαξ: +357-22481757.
PELETICO EΛΛΑΣ Α.Ε.Β.Ε.: Ζωοδόχου Πηγής 20, Χαλάνδρι 152-31,
Αθήνα, Ελλάδα, Τηλ.: +30-2106776661/2, Φαξ: +30-2106756996.

E-mail:peletico@peletico.com, URL:http://www.peletico.com.

*Παράγεται από την PELETICO LTD.,
κάτοχιν αδείας της Sherwin-Williams Company,
Κληβελαντ, Οχάιο, ΗΠΑ, κάτοχο των Εγγεγραμμένων* Εμπορικών Σημάτων.

October 2003

PELETICO

PELETICO LTD.

P.O.Box 21326, CY 1506 Nicosia, Cyprus,
Tel.: +357-22482265, Fax: +357-22481757.
PELETICO HELLAS S.A.:
20, Zoodohou Piyis, 152-31 Halandri, Athens, Greece,
Tel.: +30-2106776661/2, Fax: +30-2106756996.

*Manufactured in Cyprus by PELETICO LTD.,
under license from the Sherwin-Williams Company,
Cleveland, Ohio U.S.A., owner of the Registered* Trademarks.