


# ProMar\* 200

## Semi-Gloss Emulsion Paint



### ▶ ΓΕΝΙΚΕΣ ΠΛΗΡΟΦΟΡΙΕΣ

Το ProMar\* 200 Semi-Gloss Emulsion Paint είναι το καλύτερο επαγγελματικό ημιγυαλιστερό πλαστικό (εμάλσιον) για εσωτερική χρήση, της εταιρίας Sherwin-Williams Αμερικής. Συστήνεται, ιδιαίτερα για επιφάνειες σε κουζίνες και μπάνια.

### ▶ ΚΑΛΥΠΤΙΚΟΤΗΤΑ

Καλυπτικότητα: 13-15 τετρ. μέτρα ανά λίτρο, για κάθε χέρι.

### ▶ ΣΤΕΓΝΩΜΑ

Σε θερμοκρασία 25 °C και σχετική υγρασία 50%:  
Επιδέχεται άγγιγμα με το χέρι σε 1 ώρα περίπου.  
Επιπρόσθετα χέρια μπορούν να εφαρμοστούν σε 4 ώρες περίπου.

### ▶ ΤΕΧΝΙΚΑ ΧΑΡΑΚΤΗΡΙΣΤΙΚΑ

Τύπος Φορέα: VaVeoVa  
Ειδικό βάρος: 1.20 ± 0.02  
Ποσοστό στερεών κατά όγκο: 32 ± 2%  
Ποσοστό στερεών κατά βάρος: 46 ± 2%  
Ιξώδες: 90 K.U.  
Σημείο ανάφλεξης: > 100 °C  
Χρόνος Αποθήκευσης: 3 χρόνια

### ▶ ΠΡΟΕΤΟΙΜΑΣΙΑ ΕΠΙΦΑΝΕΙΑΣ

Καθαρίζεται η επιφάνεια από σκόνες, λάδια και άλλες ακαθαρσίες, που μπορεί να εμποδίσουν την πρόσφυση της βαφής. Επιφάνειες που είναι ήδη βαμμένες με ελαιόχρωμα, γυαλοχαρτίζονται για να σπάσει το σμάλτο και ακολουθεί ξεσκόνισμα και ξέπλυμα. Τυχόν μικρορωγμές, τρύπες από βελόνες κ.λ.π., επιδιορθώνονται με γεμιστικό ρωγμών (π.χ. Pelefilla ή Spatulina). Η επιφάνεια αφήνεται να στεγνώσει πριν το βάψιμο.

**Σοβάς:** Οι επιφάνειες σοβά πρέπει να είναι γερές, στεγνές και καθαρές. Πολύ απορροφητικές επιφάνειες πρέπει να ασταρώνονται με Masonry Conditioner ή EcoPrimer (βλέπε αναλυτικά φυλλάδια προϊόντων) και να αφήνονται να στεγνώσουν, πριν το βάψιμο. Αυτό μπορεί να επαναληφθεί, αν χρειάζεται.

**Μπετόν, τούβλα, κλπ.:** Οι επιφάνειες πρέπει να είναι γερές, στεγνές και καθαρές και να έχουν περάσει 30 μέρες τουλάχιστον από την κατασκευή τους. Τυχόν άλατα που βγαίνουν στην επιφάνεια απομακρύνονται προηγουμένως.

### ▶ ΑΣΤΑΡΩΜΑ ΕΠΙΦΑΝΕΙΑΣ

▶ Για το αστάρωμα καινούριων επιφανειών: Masonry Conditioner ή EcoPrimer (βλέπε αναλυτικά φυλλάδια προϊόντων). Επίσης, αστάρωμα μπορεί να γίνει και με αραιώση του ίδιου του υλικού με νερό, 25% κατ'όγκο περίπου.

### ▶ ΕΦΑΡΜΟΓΗ

▶ Η εφαρμογή γίνεται με πινέλο, ρολό ή σπρέι. Αραιώνεται με καθαρό νερό, αν χρειάζεται, μέχρι 10% κατά όγκο.

### ▶ ΚΑΘΑΡΙΣΜΟΣ

▶ Πιτσιλιές του προϊόντος καθαρίζονται αμέσως με νερό. Τα εργαλεία που χρησιμοποιήθηκαν καθαρίζονται με χλιαρό διάλυμα νερού: απορριπτικού.

*ΣΗΜΕΙΩΣΗ:* Οι πληροφορίες που δίνονται για τα προϊόντα μας διαμέσου των τεχνικών φυλλαδίων ή οδηγιών χρήσης, από τους υπαλλήλους, αντιπροσώπων ή προμηθευτές μας είναι βασισμένες σε εκτενή έρευνα και πολλά χρόνια πείρας και δίνονται για σκοπούς ενημέρωσης. Εγγυώμαστε τη σταθερά υψηλή ποιότητα των προϊόντων μας, αλλά δεν φέρουμε καμία ευθύνη για οποιαδήποτε ζημιά ή απώλεια παρουσιαστεί στους χώρους των εργασιών, εφόσον το τελικό αποτέλεσμα εξαρτάται και από παράγοντες που ξεφεύγουν από τον έλεγχο της εταιρίας.

### ▶ GENERAL DESCRIPTION

ProMar\* 200 Semi-Gloss Emulsion Paint is Sherwin-Williams' finest semi-gloss emulsion, designed for the professional. It is recommended for interior surfaces, especially in bathrooms and kitchens.

### ▶ COVERAGE

Spread Rate: Smooth surface: 13-15 sq m/L/coat

### ▶ DRYING

@25 °C & 50% R.H.:  
To touch - approx. 1 hour.  
To recoat - approx. 4 hours

### ▶ TECHNICAL CHARACTERISTICS

Vehicle type: VaVeoVa  
Specific Gravity: 1.20 ± 0.02  
Volume Solids: 32 ± 2%  
Weight Solids: 46 ± 2%  
Viscosity: 90 K.U.  
Finish: Semi-Gloss, 55-65 units @ 60  
Flash Point: > 100 °C  
Shelf Life: 3 years

### ▶ SURFACE PREPARATION

Remove all dirt, loose or peeling paint, grease, rust and other contaminants that may interfere with adhesion of paint. Dull glossy surfaces by using fine sandpaper or an abrasive cleaner. Clean and wash the surface. Apply an appropriate patching material (Pelefilla or Spatulina by PELETICO) to cracks, nail holes or other surface imperfections and allow to cure. Surface must be dry prior to painting.

**Plaster:** New or old plaster should be dry, cured and hard. Soft, porous or powdery plaster should be treated with Masonry Conditioner or EcoPrimer (PELETICO Products) and be allowed to dry before painting.

**Concrete and Masonry:** Must be cured and dry - generally requires 30 days after construction. Remove any efflorescence.

### ▶ SURFACE PRIMING

For priming new surfaces and for spot priming: Apply Masonry Conditioner or EcoPrimer (refer to product leaflets). Dilution of the product by 25% can also be used as a primer.

### ▶ APPLICATION

Apply with brush, roller or spray. Reduce, with water, up to 10% by volume.

### ▶ CLEAN UP

Clean up splatters and painting tools immediately with water.

*NOTE: The information supplied in our literature or given by our employees agents or distributors concerning the use of our products is based upon extensive experience and given in good faith in order to help you. We guarantee the consistent high quality of our products. However, as we have no control over site conditions or the execution of the work, we cannot accept any liability for any loss or damage which may arise as a result thereof.*

COLOR

Οκτώβρης 2003

October 2003

PELETICO

### ▶ ΠΕΛΕΤΙΚΟ ΛΤΔ.

Τ.Θ. 21326, 1506 Λευκωσία, Κύπρος,  
Τηλ.: +357-22482265, Φαξ: +357-22481757,  
ΠΕΛΕΤΙΚΟ ΕΛΛΑΣ Α.Ε.Β.Ε.: Ζωοδόχου Πηγής 20, Χαλάνδρι 152-31,  
Αθήνα, Ελλάδα, Τηλ.: +30-2106776661/2, Φαξ: +30-2106756996.

E-mail: peletico@peletico.com, URL: http://www.peletico.com.

PELETICO

### ▶ PELETICO LTD.

P.O.Box 21326, CY 1506 Nicosia, Cyprus,  
Tel.: +357-22482265, Fax: +357-22481757.  
PELETICO HELLAS S.A.:  
20, Zoodohou Piyis, 152-31 Halandri, Athens, Greece,  
Tel.: +30-2106776661/2, Fax: +30-2106756996.

\*Παράγεται από την ΠΕΛΕΤΙΚΟ ΛΤΔ.,  
κατόπιν αδείας της Sherwin-Williams Company,  
Κληβελαντ, Οχάιο, ΗΠΑ, κάτοχο των Εγγεγραμμένων\* Εμπορικών Σημάτων.

\*Manufactured in Cyprus by PELETICO LTD.,  
under license from the Sherwin-Williams Company,  
Cleveland, Ohio, U.S.A., owner of the Registered\* Trademarks.

