



PELESPEED

One-Component Synthetic Enamel Paint

Description

One-component synthetic enamel paint with excellent build, durability, gloss and colour retention for exterior surfaces. It can be applied on primed surfaces made of metal or wood.

Technical Specifications

Vehicle type	: Alkyd Resin based on Linoleic rich fatty acids
Specific Gravity	: 1.10±0.02
Weight solids	: 61±1%
Viscosity	: 5.25±0.25 Poise
Gloss	: >80 at 60°
Coverage (on a smooth surface)	: 12-14m ² /L/coat
Dilution	For brush or roller: up to 10%, by volume : For conventional or airless spray: up to 20%, by volume
Drying time at 25°C and relative humidity 50%	Touch dry: 2-3 hours : Recoat: After 12 hours, depending on weather conditions
Flash point	: <60°C
EU limit for this product (Cat. A/i): 500g/l (2010). This product contains max 490g/l VOC	

Instructions for Use

SURFACE PREPARATION

Remove all surface contamination, e.g. dust, oil stains, or other contaminants using **Thinner 11/11** (Peletico's product) and allow to dry. Peeling or cracked paint should be scraped off and sanded to a sound surface.

APPLICATION

Thinning/Cleaning: Use White Spirit for application with brush or roller and **Thinner 11/11** (Peletico's product) for application with conventional or airless spray.

Application tools: Brush, Conventional or Airless Spray.

Application Temperature: Ideal temperature for the application should be between 5-35°C and the relative humidity should not exceed 80%.

Stir well before and during use.

- On new galvanized surfaces before applying **PELESPEED**, it is recommended to apply a water based primer such as **GREY METAL PRIMER** (Peletico's product) and on new metal surfaces it is recommended to apply a solvent based primer such as **A-10 GREY METAL PRIMER** (Peletico's product).
- On new wooden surfaces before applying **PELESPEED**, it is recommended to apply a water based primer such as **WOOD PRIMER** (Peletico's product), followed by a water based undercoat such as **PELELAC UNDERCOAT** (Peletico's product).

A first coat of **PELESPEED** is then applied, followed by a subsequent crosswise coat.



Cleaning of Tools: Remove as much paint as possible from tools and clean immediately with Thinner 11/11 (Peletico's product).

PACKING: 1L, 2.5L, 4L & 20L.

COLOUR RANGE: Please refer to **Pelespeed** colour chart.

STORAGE: Store in a dry place, away from direct sunlight and/or extreme temperatures. Close the container after application.

Health and Safety Measures

- Keep out of reach of children.
- Flammable liquid and vapour.
- Causes damage to organs through prolonged or repeated exposure.
- Harmful to aquatic life with long lasting effects.
- Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.
- Keep container tightly closed.
- Wash with water and soap thoroughly after handling.
- Wear protective gloves/eye protection/ face protection.
- IF ON SKIN (or hair): take off immediately all contaminated clothing. Rinse skin with water / shower.
- Get medical advice/attention if you feel unwell and show the container or label.
- Contains: 2-BUTANONE OXIME. May produce an allergic reaction.
- Contains: Solvent naphtha (petroleum), medium aliph: Straight run kerosine, NAPHTHA (PETROL) HYDRODESULFURIZED HEAVY.
- For more information please refer to Safety Data Sheet.

WASTE MANAGEMENT

Do not empty surplus paint into drains, and do not dispose together with household refuse. Advice regarding disposal and collection should be sought from the local authorities.

Note: The information supplied in our literature or given by our employees, agents or distributors concerning the use of our products is based upon extensive experience and given in good faith in order to help you. We guarantee the consistent high quality of our products; however, as we have no control over site conditions of the executions of work, we cannot accept any liability for any loss or damage, which may arise as a result thereof.

